

Quick Drying Fatty Acid Expert!

Tung Oil Fatty Acid | Overview

Tung oil fatty acid, its main content is tung acid and small amount of linoleic acid, oleic acid and saturated fatty acid.

HS code: 3823120000, CAS No.: 506-23-0

	Indicators	Typical Parameter	Test Method
Appearance, Visual	Brown red semi transparent fluid to soft solid	Brown red semi transparent fluid to soft solid	Visual Inspection
Acid Value, mgKOH/g	180-200	190	GB/T 9104
Iodine Value, gI/100g	≥ 145	150	GB/T 5532
Unsaponifiable Substances Content, %	≤ 3	2	GB/T 5535.2

Features

High Reactivity

Quick-drying

Produced by hydrolysis, with 2% dimer and 3% tung oil content

Usages

1. For epoxy esters and alkyd resins
2. For epoxy curing agents
3. For customized product tung-linseed oil fatty acid and tung-soybean oil fatty acid

Packaging, Transport and Storage

1. Packages: plastic or iron drums (net weight 180 kg)
2. Not hazardous, flammable, keep away from ignition sources.
3. Effective storage period of one year.